DrainStar Stripdrain Specifications

DrainStar stripdrain product (DrainStar) is a two-part geocomposite drain prefabricated with a rigid polymer core covered on all sides with a non-woven, needle-punched polypropylene filter fabric. The core features a series of engineered cones that collect and move water to designated drainage exits. The fabric allows water to flow into the drain core while restricting backfill soils and other particles which may create clogs.

| Typical Property | Test Method | |
|--|---------------|-------------------|
| Drain Properties | | |
| Compressive Strength, lbs/sq ft | 6000-9000 | ASTM D1621 (Mod.) |
| Shear Strength, lbs/ sq ft | 6000/9000 | ASTM D1621 (Mod.) |
| Peel Strength, lbs/sq ft | 38 | ASTM D1876 |
| Fungus Resistance (core) | No Growth | ASTM G21 |
| In-Plane flow, gpm/ft width | 21 | ASTM D4716 |
| Hydraulic gradient = 0.1, loading = 10 psi | | |
| Unobstructed inflow area | | |
| Primary side | 85% | |
| | | |
| Fabric Properties | | |
| Material | Polypropylene | |
| Grab Tensile Strength, lbs | 110 | ASTM D4632 |
| Puncture Strength, İbs | 65 | ASTM D4833 |
| Trapeziodal Tear, lbs | 50 | ASTM D4533 |
| Mullen Burst Strength, psi | 215 | ASTM D3786 |
| Elongation, % | 60 | ASTM D4632 |
| EOS (AOS) | 100 sieve | ASTM D4751 |
| Permeability, cm/sec | 0.30 | ASTM D4491 |
| Flow Rate, g/min/sq ft | 150 | ASTM D4491 |
| UV Resistance, (After 500 hours) | 70% | ASTM D4355 |
| Fungus Resistance | No Growth | |
| | | |

Dimensional Data

Thickness Standard Widths Roll Weight

1 inch min. 12 inches min. 200 lbs

For more information on DrainStar, talk to your Barrier Solutions Contractor or call Tremco Barrier Solutions. 800-DRY-BSMT www.guaranteeddrybasements.com