



MONDUR[®] MR-LIGHT

Polymeric MDI

CAS No. 9016-87-9

Product Code: G172-1000

Description

Mondur MR-Light is a polymeric diphenylmethane diisocyanate (PMDI) that is used in the manufacture of polyurethane foams, binders, adhesives, and elastomers. As with any product, use of Mondur MR-Light isocyanate in a given application must be tested (including but not limited to field testing) in advance by the user to determine suitability.

Typical Properties*

Property	Value
Appearance	Brown liquid
NCO, Wt. %	31.8%
Acidity Wt. %	0.02%
Viscosity** at 25°C	200 mPa·s
Specific Gravity at 25°C	1.24
Flash Point, PMCC	199°C

Storage

Mondur MR-Light isocyanate must be stored in tightly closed containers and protected from contamination with moisture and foreign materials, which can adversely affect processing. Storage temperatures should be maintained between 18° and 30°C (64° and 86°F).

Health and Safety Information

Appropriate literature has been assembled which provides information concerning the health and safety precautions that must be observed when handling Mondur MR-Light isocyanate. Before working with this product, you must read and become familiar with the available information on its hazards, proper use, and handling. This cannot be overemphasized. Information is available in several forms, e.g., material safety data sheets and product labels. Consult your Bayer MaterialScience representative or contact Bayer's Product Safety and Regulatory Affairs Department in Pittsburgh, Pa.

* These items are provided as general information only. They are approximate values and are not considered part of the product specifications.

** Brookfield viscosity method.

Note: The information contained in this bulletin is current as of May 2002. Please contact Bayer MaterialScience to determine whether this publication has been revised.

Bayer MaterialScience LLC

100 Bayer Road • Pittsburgh, PA 15205-9741 • Phone: 1-800-662-2927 • www.BayerMaterialScienceNAFTA.com

The conditions of your use and applications of our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance and information to determine to your own satisfaction whether they are suitable for your intended uses and applications. This application-specific analysis at least must include testing to determine suitability from a technical as well as health, safety and environmental standpoint. Such testing has not necessarily been done by Bayer all information is given without warranty or guarantee, and is subject to change without notice. It is expressly understood and agreed that the customer assumes and hereby expressly releases Bayer from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance and information. Any statement or recommendation not contained herein is unauthorized and shall not bind Bayer. Nothing herein shall be construed as a recommendation to use any product in conflict with patents covering any material or its use. No license is implied or in fact granted under the claims of any patent.

